

### 1.0 SCOPE

This document establishes the specification requirements for an indoor/outdoor distribution fiberoptic cable. This cable construction consists of multimode fibers in a distribution tight-buffered design with a riser rated PVC jacket.


### 2.0 APPLICABLE DOCUMENTS

Reference Documents: TIA/EIA FOTP Standards 455  
Color Coding of Fiber Optic Cables TIA/EIA-598  
UL 1666  
GR-409-CORE

### 3.0 REQUIREMENTS

This document contains test values for all-important mechanical, optical, and environmental parameters and as such, is the basis for all-incoming inspection and acceptance.

### 4.0 CABLE CROSS SECTION *(Representation of a 48 fiber cable)*



### 5.0 OVERALL CABLE CONSTRUCTION

#### 5.1 Tight Buffered Fiber

Dimension: 900µm, nominal.

Tight buffered fiber color code: 1-blue, 2-orange, 3-green, 4-brown, 5-slate, 6-white, 7-red, 8-black, 9-yellow, 10-violet, 11-rose, and 12-aqua.

5.2 Sub-unit consists of water swellable aramid yarns that are pulled in with the tight-buffered fibers under a sub-unit jacket. The subunits are colored per TIA/EIA-598 or orange and are numbered for identification.

#### 5.3 Cable strength Member

Fiberglass Epoxy Rod (dielectric)

An up coat of PVC (if necessary per construction for symmetry).

#### 5.4 Cable Core

Sub-units and fillers (if needed) are stranded around the CSM, using reverse oscillation.

Binder yarns are applied over the cable core.

#### 5.5 Outer Sheath

UV Resistant Black riser rated PVC jacket (or color per customer request)

#### 5.6 Cable Markings

REMFO 11 SERIES, FIBER OPTIC CABLE, XX (denotes number of fibers)-50/125, REMEE PRODUCTS CORP., MM/YY (month & year of manufacture), OFNR C(ETL)US, Sequentially marked.

Special print as required by customer.

5.7 Nominal Cable Dimensions & Weights

Remeer Products Part Number	No. of Fibers	Cable OD (mm)	Cable OD (in.)	Weight KG/KM	Weight LB/1000ft
11-018-12C-GBSFXF	18	13.7	0.540	142	96
11-024-12C-GBSFXF	24	13.7	0.540	142	96
11-036-12C-GBSFXF	36	16.8	0.660	221	148
11-048-12C-GBSLXF	48	16.0	0.628	198	133
11-060-12C-GBSLXF	60	17.7	0.696	233	157

6.0 FIBER CHARACTERISTICS

6.1 Physical Parameters (nominal)

Fiber Type	Multimode*
Maximum Attenuation @ 850/1300nm**	3.0 /1.0 dB/km
Minimum Bandwidth @850/1300nm	500/500MHz-km
Core Diameter, nominal	50 ± 2.5 µm
Cladding Diameter	125.0 ± 2.0 µm
Primary Coating Diameter	245 ± 10 µm
Cladding Non-circularity	<1%
Core-Clad Concentricity	≤1.5 µm
Zero Dispersion Wavelength	1300-1320nm
Numerical Aperture	0.20 ± .015
Group Refractive Index @ 850/1300nm	1.483/1.478
Proof Test	100 kpsi

\*Guaranteed Gigabit Ethernet Distance of 600/600mtr at 850/1300nm for 1 Gb/s per IEEE802.3z.

\*\*Measured attenuations on shipping reels will not exceed the nominal values by .75dB/km.

7.0 MECHANICAL & ENVIRONMENTAL PERFORMANCE

Maximum Tensile Load for:

Installation: 2700N / 607lbf

Long Term: 890N / 200lbf

Minimum bending radius:

Loaded: 20 x diameter

Unloaded: 10 x diameter

Crush Resistance: 220N/cm

Impact Resistance: 25 Impacts (min.)

Flexing, ±90°: 25 Cycles (min.)

Temperature Rating:

Operation, -40°C to +85°C

Installation, 0°C to +75°C

Storage, -55°C to +85°C

8.0 PREPARATION FOR DELIVERY

The cable shall be packaged to preclude the inducement of damage due to handling and transportation, and shall be in accordance with the best commercial practices available.



1751 State Rte. 17A Florida, New York 10921  
800 431-3864